

Product Data

Product Description:

I-POW-C is a free-flowing powder material that easily disperses in plastic and elastomeric matrices. It is produced from end-of-life tyre.

Specifications

Properties	Test method	Values	Units
Particle size	Sieve test method	%20-25	125 Mesh
Particle size	sieve test method	%50-55	180-250 Mesh
Particle size	sieve test method	%10-15	355 Mesh
Particle size	sieve test method	%0-8	> 355 Mesh
Metal Content	ASTM D5603	< 0.1	wt. %
Fiber Content	ASTM D5603	< 0.2	wt. %
Ash (Silica) Content	ASTM D297-18	18 – 24	wt. %
Specific density	Pycnometric method	1150	kg/m ³
Moisture Content	Internal method	< 1	wt. %

Packaging Type:

Bags: 25 kg

Other packaging options available on request at additional fee

ICARBON Kimya Arge Müh.San.ve Tic. Ltd. Şti

Görükle Mah. Üniversite-1 Cd. ULUTEK Teknoloji
Geliştirme Binası No:933/B016

Nilüfer / BURSA /TURKEY

Tel: +90 535 366 65 34

Mail: info@icarbon.com.tr

<https://www.icarbon.com.tr/>

The information in this document has been prepared in the light of laboratory information obtained at the time of publication. The document is designed to provide users with general information on safe use, processing, storage, transportation. Nothing herein should be considered a warranty unless otherwise stated. In all circumstances, it is the user's responsibility to evaluate this information and recommendations with the suitability of each product for its specific use. ICARBON Kimya Arge Müh.San.ve Tic. Ltd. Şti cannot be held responsible.

